# A novel alumina and carbonate production method from aluminium rich materials with integrated CO<sub>2</sub> utilization

## Background of the invention.

Alumina (Al<sub>2</sub>O<sub>3</sub>) for production of aluminum is largely produced from bauxite (more than 95wt%).

- 5 However, in recent years, the availability of good grade bauxite has diminished and the price has correspondingly increased. The bauxite processing generates environmental problems (e.g. red mud) particularly when processing lower grade bauxite. For these reasons, considerable interest has been put on production of alumina from aluminum rich silicate rocks, such as anorthosites, nepheline syenites and feldspar/feldspathoid minerals derived from such rocks, as it is known that
- 10 these rocks and minerals can be dissolved directly in strong mineral acids, without any costly pretreatment step, such as high temperature roasting.

Particularly anorthosites, with high anorthite content have received much attention, an example being Norwegian patent No. 323417 (Eriksen et al.). Lately sedimentary rocks, such as argillite (clay/mudstone) have also received considerable interest.

- 15 'Anorthosite' is a collective term for igneous rocks characterized by a predominance of plagioclase feldspar (90-100%), and a minimal mafic component (0-10%). The plagioclase feldspar series contains a variety of Na-Ca-Al silicates between the two end members albite (NaAlSi<sub>3</sub>O<sub>8</sub>) and anorthite (CaAl<sub>2</sub>Si<sub>2</sub>O<sub>8</sub>). Norway has abundant occurrences of anorthosite, some with high anorthite content (70 to 80%) located at the western coast. Due to the high alumina content (Al<sub>2</sub>O<sub>3</sub> >30%) in
- 20 the Gudvangen deposit (estimated at ≥ 500M Tonnes of anorthosite) located in Sogn og Fjordane, recovery of alumina from Norwegian anorthosite has been subject to extensive studies.

One of the largest research efforts was invested into the Anortal project (1976-1987), a process to produce alumina from anorthosite, based on leaching or dissolving the mineral with a mineral acid and the subsequent precipitation of aluminium trichloride hexahydrate (AlCl<sub>3.</sub>6H2O) from the acid

- 25 phase. A technological path for a nitric acid route was patented (US4110399 A) by the Institutt for Atomenergi (now IFE). The technological concept was later developed and patented by Eriksen et al. as Norwegian patent No. 323417. The process according to this patent relies on leaching with nitric acid followed by subsequent solvent extraction of unwanted species (Fe, Ca) and partial acid recovery.
- 30 Worldwide, other attempts have been made to obtain alumina by alternative process different from Bayern:

US patent No. 4 110 399 (Gaudernack et al., 1978) shows a process for extraction of alumina from Al containing silicates involving leaching with sulphuric acid, extraction of iron into an organic

phase while leaving Al ions in the aqueous phase, precipitation of Al as aluminium chloride hexahydrate and subsequent calcining.

US patent No- 4,367,215 claims the production of silica with controlled properties by acid leaching of silicates, but limits the scope to the silica product and with no technological solutions for

5 alumina or carbonates production, acid recovery, iron separation, etc.

CA patent No. 2,711,013 A1 proposes an invention for the obtaining of Al from aluminous ores, by initial dissolution of the ore with acid, but focusing on the later separation of aluminium and iron ions to produce iron-rich concentrate and the later extraction of aluminium by organic extraction. Therefore, neither a sparging step for the initial aluminium separation, nor the CO<sub>2</sub> use for

10 carbonates precipitation and nor the acid recovery by amines thermal treatment are considered in that process.

US Patent application No.2009/022640A1 proposes a process where sulfuric acid is used for leaching the aluminium-containing solid and the later use of hydrochloric acid during the sparging step is done at a temperature under 20°C.

- US patent application No. 2012/0237418 A1 (Boudreault, Alex and Biasotto) describes a process to obtain aluminium by leaching with hydrochloric acid (the pressure is not specified) and the later separation of iron from aluminium by several pH-controlled stages by using organic extractants, therefore focused in high iron content aluminium ores (e.g. argillite, nepheline). The aluminium and iron separation follow different methods and the use of CO<sub>2</sub> and carbonate production nor the
- 20 acid regeneration are mentioned.

US patent No. 4,158,042 proposes the dissolution of the Al-rich mineral with a leaching liqueur containing chloride, calcium and fluoride ions, this last used as reaction catalyst (in the form of  $H_2SiF_6$  and in a quantity of 1-20gms/liter). When applied to a Ca-rich rock (anorthosite), they propose the precipitation and separation of part of the CaCl<sub>2</sub> and the combination of this CaCl<sub>2</sub>

25 with silica at high temperature (1100°C) to recover part of the HCl. This sub-process for acid recovery is very energy demanding, with a highly negative impact on the possible profitability of the process.

For the separation of Al from the leaching liqueur, John E. Deutchman and Francoise Tahiani (US patent No. 4,472,361, 1984) reported a method to separate Al and Na from a starting solid mixture of AlCl<sub>3</sub> and NaCl (coming from a quantitative precipitation by a first sparging) applying a selective

30 of AlCl<sub>3</sub> and NaCl (coming from a quantitative precipitation by a first sparging) applying a selective redissolution of the AlCl<sub>3</sub> in water, to produce an aqueous AlCl<sub>3</sub> solution with a reduced Na concentration, and a solid NaCl product that can be separated by filtration. A second sparging with HCl gas is used to re-precipitate AlCl<sub>3</sub> from the aqueous solution. After separation of the AlCl<sub>3</sub> (i.e.

ACH), the concentrated HCl solution is recirculated to the process in the first sparging step, while the solid ACH is sent to the calcination process step.

For the separation of iron, in US patent No. 5,585,080, a method for recovering metal chlorides from silicon and ferrosilicon is described. In that work, TBP was applied for iron chloride

5 extraction, directly after the leaching of the material, from the acid solution containing high AlCl<sub>3</sub> and CaCl<sub>2</sub> concentrations, followed by sparging of HCl gas to recover aluminium chloride. After removal of FeCl<sub>3</sub>, the leachate consists of a concentrated HCl solution with metal chlorides such as CaCl<sub>3</sub>, MgCl<sub>2</sub>, NaCl.

Regarding the recovery of the process acid, several patents present the possibility of using organic
 extraction (with different amines) to extract free HCl from diluted solutions and for the later
 recovery of concentrated HCl by stripping of the amine (Baniel and Jansen, US patent application
 No. 2012/0134912; Baniel and Eyal, US patent application No. 2010/0093995, US patent
 application No. 2011/0028710 and EP 2 321 218 A1; Baniel, Eyal and Jansen, WO 2010/064229 A2;
 Coenen, Kosswig, Hentschel and Ziebarth, US patent No. 4,230,681; Willi Ziegenbein, Ferdinand

- von Praun, US patent No. 4,272,502 A; DeVries, US patent No. 4,640,831 A). These publications are applicable for the recovery of free HCl in solution, but not for recovering Cl<sup>-</sup> ions from metal
   chlorides with precipitation of the corresponding -metal carbonate . Other authors have proposed the CO<sub>2</sub> utilization for the precipitation of sodium bicarbonate (Hentschel, Coenen, Kosswig, von Praun and Ziebarth US patent No. 4,337,234; Coenen, Laach, Kosswig, von Praun and Hans Regner
- US patent No. 4,321 247 A; Hentschel, Jürgen, Coenen, Kosswig, Ferdinand von Praun US patent
   No. 4,320,106A), and for the production of ammonia from ammonium chloride (Coenen, Laach,
   Kosswig Dieter US patent No. 4,305,917), but not tackling the later acid recovery from the amine.

The most recent patent application related to alumina production - WO 2013/037054 A1 is based on the well-known generation of dissolved metal chlorides by the leaching of an aluminium-rich

- 25 material with HCl, and the later re-precipitation of the metal chlorides by sparging with HCl. Then, the acid recovery is achieved only by the calcination of the diverse metal chlorides obtained along the process (AlCl<sub>3</sub>·6H<sub>2</sub>O, FeCl<sub>3</sub>· xH<sub>2</sub>O, MgCl<sub>2</sub>·xH<sub>2</sub>O, etc.) to evolve the HCl as a gas and produce metal oxides. However, low total HCl recovery can be expected if this process is applied to any Alcontaining materials that have a high Ca-content since the hydro-pyrolysis of CaCl2 is difficult due
- 30 to its low melting point and the high decomposition temperature of CaCl<sub>2</sub>·2H<sub>2</sub>O. Additionally, no technological solution is given for the efficient separation of sodium if the ore contains this element, which would precipitate as NaCl together with the aluminium chloride during the sparging step. This means that applying this method to e.g. anorthosite, would be doubtfully economic, due to its considerable calcium and sodium content. So technically, several Al-rich could

be treated following WO 2013/037054 A1 steps, but obviously only some minerals – especially those rich in iron and magnesium - are the most appropriate raw materials that could bring a competitive process. As in the previous alumina production patented alternatives, the use of CO<sub>2</sub> and the recovery of extra HCl while producing carbonates from the remaining chlorides in solution is not mentioned.

5 is not mentioned.

Therefore, although some of the alternative process concepts succeeded with respect to product recovery, either the economic viability of those technologies proved unfavorable in comparison to the already well-established bauxite Bayer process and/or focused on only parts of the process or did not tackle acid recovery as to make it applicable for varied aluminium sources.

10

20

### **Objective.**

It is an object of the present invention to provide an improved method for obtaining alumina from aluminium-rich materials in a sustainable, cost effective and environmentally friendly manner. It is also an object of the invention to combine the production of raw material for aluminium with a

15 method/process, where the greenhouse gas  $CO_2$  is immobilized by the production of a metal carbonate that can be safely deposited or commercialized.

Finally it is also an object of the invention to produce amorphous  $SiO_2$  which can either be safely deposited or, at least partially, commercialized.

Thus the present invention should not strain the environment by generating toxic solid or liquid waste materials

# The present invention.

The present invention presents a new technology integrated in a unique way to accomplish today's environmental and economic targets by an innovative process for alumina production with

25 integrated CO<sub>2</sub> utilization.

The above mentioned objectives of the present invention are realized as defined in claim 1. Some preferred embodiments of the invention are given by the dependent claims.

This invention is a new method for production of alumina from aluminum rich materials, which in terms of cost efficiency and environmental impact can compete with bauxite. The invention has an

30 added focus on the possibility of achieving environmentally benign CO<sub>2</sub> storage by precipitation of carbonates from aqueous metal-containing process streams, originating from the Al-rich material leaching or partial dissolution.

The present invention as a global process differs from the previous attempt developed by Institutt for Atomenergi (US patent No. 4,110,399 A) in the following aspects:

- The proposed acid for the leaching (and subsequent process steps) is hydrochloric acid, instead of sulfuric acid.

5 -A different technological solution is proposed to minimize the impurities of Al<sub>2</sub>O<sub>3</sub> and the energy consume in the sparging step, by including the step-wise sparging process with possible re-dissolutions and re-precipitations of AlCl<sub>3</sub>.

- When applied to metal<u>calcium</u>-rich materials that can form carbonates,  $CO_2$  can be utilized, as a  $CO_2$  safe storage or as a commercial byproduct, instead of the gypsum production (CaSO<sub>4</sub>) claimed

10 in US patent No. 4110399 A from anorthosite. Therefore,  $CO_2$  in introduced in this the present invention as a key factor, both for environmental and economic reasons.

- The combined carbonate production and acid extraction presented here introduces a new technology in the process, to enhance the total acid recovery and so improve the economics of the invention.

15 For a better understanding of the present invention, there have been included schematic process layouts that simplify the process into core process steps, and show the invention with some preferred embodiments as an example.

Figure 1 shows a simplified process scheme according to one preferred embodiment of the present invention.

Figure 2. shows a simplified process scheme of the present invention according to the embodiment in claim 10, where the iron removal step (80) is included, to avoid high iron content in the produced precipitated calcium carbonate.

Figure 3. Shows the proposed sub-process for the separation of aluminium from the leachates by sparging step (3b), in comparison to Deutchman and col. technology (US patent No. 4,472,361,

25 1984) (3a).

Figure 4. Shows another preferred embodiment for the sparging step for the separation of aluminium from the leachates (4b), in comparison to Deutchman and col. Technology (US patent No. 4,472,361, 1984) (4a).

Thus, in the present invention simplified in Figures 1 and 2, the Al-rich material is crushed and
milled to a size less than 20 mm and preferably to a size under 1 mm, more preferred equal or
under 0.5 mm. Fe and Mg rich fractions may be removed after the crushing, at least in part, by

magnetic separation, or preferably removed by optical sorting. It is thus possible to obtain a material powder with reduced content of iron and magnesium. The prepared material is then dissolved directly in a HCl solution, at a concentration in the range 1 to 13 M, at a temperature in the range 80°C to 180°C, and a pressure of up to 10 bars for 1 to 24h according to the reaction (1).

5 More preferred the temperature is under 160 °C, the pressure is less than 5 bar and the leaching time is in the range 1 to 10 hours or even more preferred in the range 1 to 5 hours.

A simplified leaching reaction for an ideal Al-rich material may be represented as an example by the anorthite theoretical composition, according to the following equation:

$$CaAl_2Si_2O_8(s) + 8 H^{+}(aq) \rightarrow Ca^{2+}(aq) + 2 Al^{3+}(aq) + H_8Si_2O_8(aq)$$
 (1)

10 The operating conditions defined above were chosen to optimize the dissolution of  $AI^{3+}$  and other cations from a silicate (e.g.  $Ca^{2+}$ ,  $Mg^{2+}$ ,  $Na^+$ ) while producing an amorphous SiO<sub>2</sub> residue with the required properties for commercialization or deposition.

Since the silicate rocks are completely leached in HCl, the present invention also allows for production of amorphous precipitated silica, as the solid fraction remaining from the leaching.

15 The use of HCl ensures the formation of solubilized metal chlorides in the mother liquor which can be further separated by sparging of HCl gas, contrary to other inventions above mentioned that use different leaching solutions.

After dissolution, solid residues, for example unreacted particles and SiO<sub>2</sub>, are separated from the leachate by centrifugation and/or filtration. Unreacted fractions may be separated by density or

20 other differentiating properties, e.g, by using hydro-cyclones. After separation, unreacted fractions can be reintroduced to the acid leaching step.

After separation of the undissolved fraction, the acid leachate containing mainly Al<sup>3+</sup> and Ca<sup>2+</sup> is sent to a second process step: The aluminium chloride precipitation by sparging (bubbling) of a gas flow containing HCl.

- 25 Aluminium can be precipitated from the leach liquor by sparging of an hydrogen chloride containing gas in the solution, utilizing the common ion effect, i.e. promoting the precipitation of hydrated aluminium chloride, AlCl<sub>3</sub>·6H<sub>2</sub>O (ACH) by increasing the chloride ion concentration in the solution. Hydrogen chloride gas dissolves readily in the mother liquor, over a wide range of temperatures at atmospheric pressure. Due to its lower solubility limit, aluminium chloride (and,
- 30 at some extent, sodium chloride if present) will precipitate as hydrated salt while Fe<sup>2/3+</sup>, Ca<sup>2+</sup> and Mg<sup>2+</sup> or other more soluble metal chlorides remain mainly in solution.

Other technologies had been proposed to reduce the amount of NaCl impurities in the final product when the leachate from the material contains sodium, including the later washing and re-

calcination of the precipitated alumina (US Patent 4,472,361, 1984). These processes have the problem of having a high energy cost due to consecutive cooling and heating steps of large quantities of solids.

In the present invention, a new process has been developed under two preferred embodiments

- 5 for the sparging and impurities elimination, based on the common ion effect that was experimentally observed by Deutchman and Tahiani. The new alternatives are compared to Deutchman and Tahiani's process in Figures 3 and 4, where 3a) and 4a) are Deutchman's technology and 3b) and 4b) are the two preferred embodiments for the new alternatives developed for the present invention.
- 10 In Figure 3b, where a box is divided by a diagonal line into halves marked as S and L, this means that the step involves separation of the mixture into a liquid and a solid fraction. The first preferred embodiment modifies steps 10, 20 and 30 from Deutchman (Figure 3a)), by purging the calcium chloride rich liquid out of the sparging system (step 20), instead of recycling it to step 10. This purge solves the problem of impurities accumulation in the system that would affect
- 15 Deutchman's configuration. Indeed, the increasing concentrations of Ca<sup>2+</sup>, Mg<sup>2+</sup>, Fe<sup>2+</sup>/Fe<sup>3+</sup> in the recycling loop would on the long term affect the ACH purity. Another advantage of the proposed embodiment 1 is the possibility to recover HCl from the Ca, Mg or other chloride-rich stream by production of the corresponding carbonates utilizing CO<sub>2</sub>, in addition to the HCl recovery from the AlCl3 calcination (step 70). Another modification proposed in the modified sparging process is the
- 20 use of acidic solution to partially redissolve the NaCl/AlCl<sub>3</sub> solid, instead of using only pure water (step 30). This alternative is preferred based on the bigger solubility differences of AlCl<sub>3</sub> and NaCl in HCl, compared to water.

Deutchman and Tahiani propose a total precipitation of ACH and NaCl by a first sparging of the leachates obtained from the solid mixture of ACH and NaCl, which they partially redissolve to

eliminate most of the solid NaCl (Figures 3a)and 4a)). Another alternative preferred embodiment is presented in the present invention where it is proposed to perform a fractional or multi-stage precipitation process (Figure 4b).

Thus, in the second proposed embodiment it is proposed a partial precipitation of ACH in the first sparging step (20). In this first partial sparging step, almost pure ACH is obtained until a certain

30 limit of precipitate production, at a temperature between 40 and 90°C, preferably between 60 and 80°C. This first sparging step is stopped before NaCl starts precipitating quantitatively. This means that a quantitative fraction of almost pure ACH will precipitate in step 20, leaving most of the NaCl in the solution. The remaining liquid is sent to a second sparging step where the

remaining ACH fraction and most of the NaCl can be precipitated and further treated (40) –by Deutchman and Tahiani method or similar - to eliminate the NaCl impurities of this second precipitate. The redissolved ACH can be sent to the first sparging step (20). Several consecutive NaCl redissolution and sparging steps may be needed to reach a suitable alumina grade depending

5 on the application of the Al2O3. The solid NaCl separated can be used as feed for a chlor-alkali electrolysis cell for recovering HCl and producing NaOH, or can be sold as a byproduct. The product from step 20 will be send directly to the calcination (50) and, if needed, to the wash and drying steps (60, 70).

After physical separation and washing, the solid ACH is heated step-wise, first at a temperature

10 between 400 and 600°C using an indirectly heated calciner, to decompose the ACH and produce a HCl-rich gas that can be recycled to the sparging step. The produced aluminium hydroxide is further sent to a second calcination step operating at higher temperature, over 600°C, preferably between 900 and 1100°C, to convert the hydroxide into the final aluminium oxide (Al<sub>2</sub>O<sub>3</sub>).

After the sparging process, the remaining liquor is a concentrated HCl solution containing the

remaining metal chlorides (e.g. Ca2+, Mg2+, Na+). This liquid stream is further processed to recover HCl with  $CO_2$  utilization for carbonates production.

However, due to the somewhat heterogeneous nature of the materials, the leachate may have a higher level of  $Fe^{2+}/Fe^{3+}$  than can be tolerated in the final carbonate product. If this is the case, iron can be removed by a similar liquid-liquid extraction process to that suggested in NO323417 and US

5,585,080 patents, by using an organic solution, not mixable with water, containing for example, bis (2-ethylhexyl) hydrogen phosphate (Eriksen et al, 2007, Norwegian patent No. 323417) or as in the Anortal-process (US Patent No. 4,110,399).

The use of a diluted organic extractant has been shown to be an efficient media to remove  $Fe^{2+}/Fe^{3+}$  from a concentrated HCl solution. When contacted with an iron containing liquor, Tri-

25 butyl phosphate (TBP) diluted in a hydrocarbon solvent selectively extracts Fe<sup>3+</sup> cation. In the second stage, TBP is regenerated by contacting the loaded solution with acid or water, stripping the metal chlorides from the organic solution before recycling to the extraction stage.

If desirable, HCl can be recovered from the concentrated solution of  $FeCl_3/FeCl_2$  by pyrolysis or hydrolytic distillation (as proposed in EP 2 310 323 B1), thus producing  $Fe_2O_3$  that can be commercialized depending on the purity.

30

This solution is sent to a process step where free HCl is recovered by heating the solution above the boiling temperature of HCl/Steam. This process steps benefits from the high chloride salts

concentration in the solution, as it acts as "azeotrope breaker" and reduce the energy penalty of the process step. A mixture of HCI/steam is recovered producing a hydrochloric acid solution which can be recirculated in the process. The remaining solution after acid recovery is a concentrated metal-chlorides solution with as low as possible free HCI concentration.

5 Several patents present the possibility of using organic extraction (with different amines) to recover HCl from diluted solutions and the recovery of concentrated HCl by stripping of the amine

Contrary to prior art methods (Baniel and Jansen, US patent application No. 2012/0134912 and others) the present invention makes use of  $CO_2$  in the process of HCl recovery at least partly due to the environmental benefit of  $CO_2$  utilization for carbonates production that characterize the present invention.

The innovative process step proposed here aims at recovering HCl from a  $metal_{calcium}$  chloride rich solution with  $CO_2$  immobilization by forming a carbonate. The technology based on amine extraction is applied to the remaining solution after distillation of the free acid. In this step, the solution with  $metal_{calcium}$  chlorides is contacted with an organic solution containing at least one

- amine diluted in a hydrocarbon solution. The mixture of the aqueous and the organic solution is mechanically mixed in a tight reactor which is pressurized with a CO<sub>2</sub> containing gas at a pressure of at least 2 bars. Under pressurized conditions the CO<sub>2</sub> dissolves in the aqueous phase and reacts
   with the metal<u>calcium</u> chloride and the amine to produce the corresponding metal<u>calcium</u> carbonate (that precipitates) and an ammonium chloride complex (that remains in the organic
- 20 phase). As an example,) as illustrated by the reaction for 2-valent metallic cations is the followingequation:

 $\frac{\mathsf{MCl}_2\mathsf{CaCl}_2}{\mathsf{CaCl}_2} + 2\mathsf{R}_3\mathsf{N} + \mathsf{CO}_2 + \mathsf{H}_2\mathsf{O} \twoheadrightarrow \mathsf{M}_{\underline{\mathsf{Ca}}}(\mathsf{CO}_3) + 2\mathsf{R}_3\mathsf{N} \cdot \mathsf{HCl}$ (2)

10

Where M represents the metal chloride in solution and where R3N a tertiary amine complex where R3 is a carboxylic chain ( $C_6$ - $C_{12}$ ).

25 Tertiary amines with more than 6-carbons are not soluble in water and are therefore prefered in this invention. Tertiary amines with less than 6C chains are partially soluble in water whilst their respective ammonium chloride salts are totally water soluble, thus not suitable for the application

Since the aqueous phase and the organic phase are not miscible, the two phases rapidly separate when the stirring stops. The solid precipitated carbonate remains in the aqueous phase and can

30 easily be separated by filtration, while the amine loaded with HCl can be sent to a stripping step to regenerate the HCl and the amine solution.

Multi-step counter-current configuration can be necessary to reach high recovery efficiencies. In this case, two or more consecutive reactors in counter-current mode might be considered to increase the overall acid recovery as calculated from experimental data shown in Example 3.

After extraction, the amine loaded with HCl must be regenerated. A preferred option would be to

- directly distillate the amine by heating the organic phase at a temperature between 50 and 300°C, most preferred between 50 and 150°C, if necessary with a carrier gas such as steam or inert gas, to
   produce an HCl-rich gas, as presented in EP2321218EP 2321218 A1 and US 4230681. Such technology has been previously proposed for regeneration of carboxylic acids in bioreactors for free HCl recovery in diluted acid streams [PCT/IL2009/000392]. The proposed embodiment herein
- 10 is the first reported process for HCl regeneration from dissolved metallic chlorides solution produced by acid leaching of Al-rich materials.

Direct distillation of the amine to recover HCl gas, pure or mixed with steam or other carrier gas, is the preferred technological path as the produced gas can be readily recirculated to the process or stripped in an absorption column to produce directly concentrated hydrochloric acid.

15 Another preferred alternative is to contact the HCl-loaded amine with a strong basic solution, like for example NaOH or KOH, to regenerate the amine which can be recirculated to the carbonate precipitation step and producing a concentrated NaCl solution which can fed to chlor-alkali electrolyser to produce concentrated solution of hydrochloric acid and NaOH.

After precipitation of the carbonates, the aqueous phase can contain low concentration of other
 secondary metal chlorides. The aqueous phase can either be further treated to recover HCl from
 those metal chlorides or considered as waste water and deposited after appropriate treatment to
 match environment-friendly conditions.

Now reverting more in detail to the drawings. Fig. 1 shows a simplified process scheme according to one preferred embodiment of the present invention.

25 The process diagram has been simplified, and the different steps with a common purpose have been grouped in blocks:

Step 20 might involve 2 or more consecutive washing and filtering steps with acid and/or water;
the new technology for the sparging (30) has been explained in detail with two preferred embodiments in figures 3b) and 4b), in comparison with previous technology 3a) and 4a)

30 presented by other authors;

- the calcination (40) might be carried out in two consecutive ovens at different temperatures for a better total acid recovery:,

the acid recovery (50) might involve an several equipment units (e.g. evaporator and flash unit);
the precipitation might need more than one step, carried out with countercurrent reactors and including phases separation in between reactors, and the amine and acid regeneration can be achieved by different technologies, as mentioned in the claims.

5 Figure 2. shows a simplified process scheme of the present invention according to the embodiment in claim 10, where the iron removal step (80) is included to avoid high iron content in the produced PCC.

Such a process comprises various process steps that are explained below in detail with reference to Figure 1.

- 10 In general the process may be seen to comprise at least the following stages.
  - 1) Physical preparation of the Al-rich material.
  - Acid leaching of Al<sup>3+</sup> and other cations as carbonate promoters from the material, Liquid and solid recovery.
  - Multi-stage precipitation of AlCl<sub>3</sub>·6H<sub>2</sub>O (ACH) from the aqueous leachate by sparging of dry HCl gas
  - 4) Calcination of ACH for HCl gas regeneration and production of Al<sub>2</sub>O<sub>3</sub>
  - 5) Iron extraction by liquid/liquid separation method (optional)
  - 6) Acid recovery by evaporation of free HCl from the leachate
  - Precipitation of carbonates from metal-chlorides-rich solution with combined HCl extraction
  - 8) HCl and amine regeneration from the loaded organic solution.

1) Physical preparation of the silicate rock. Figure1 - Step 00

The Al rich source material, for example anorthosite, can be selectively mined. Contaminating side

- 25 fractions or layers/bands can be optically sorted. The physical preparation of the material includes;
  - a) Crushing and milling to less than 0.5 mm diameter size fraction.
  - b) If necessary, iron and magnesium containing fractions are removed by optical sorting, magnetic separation or other suitable method known in the art.

# Acid leaching of Al<sup>3+</sup> and other metallic ions from the material, - Leachate and SiO2 recovery. Figure1 - Step 10 and 20

20

The crushed and pretreated material is dissolved in HCl acidic solution (1 to 13M) in a dissolution reactor at 80°C and 160°C at atmospheric pressure or pressurized conditions up to 10 bars.

After dissolution in the leaching step, solid residues (unreacted fractions and  $SiO_2$ ) are separated from the leachate by centrifugation and/or filtration. In the process scheme, unreacted fractions

- 5 may be separated from the amorphous SiO<sub>2</sub> product, e.g. by density/ grain separation techniques using hydro-cyclones in series or parallel or any other suitable separation technique known in the art. After separation, unreacted fractions may be reintroduced to the acid leaching step. Also unreacted acid leaving the leaching reactor may be at least partially recovered by flash evaporation and recycled to the leaching step.
- SiO<sub>2</sub> product may be washed by use of diluted acid and water washing steps organized in a counter current manner to remove traces of dissolved cations and HCl and produce a commercial product. Optionally, further chemical treatment of SiO<sub>2</sub> can be performed to reach higher purity in the product.

In practice the leaching step may be arranged in a number of different ways, ranging from single

- batch process- one or several leaching reactors operating in parallel, depending on the production rate necessities to a multiple batch configuration using leaching reactors interconnected in series depending on the material dissolution kinetics. For high-reactivity ores where the leaching time is realistic for industrial scale, the preferred configuration is the single batch process, that can be performed in parallel reactors if high volumes are processed. As described in Example 1, the one-
- 20 batch configuration has been successfully proved at pilot scale using anorthosite. Laboratory tests have also shown that consecutive batches and for semi-continuous leaching (by partially substituting the leachates for fresh acid during the process) can be beneficial for increasing the dissolution kinetics and reduce the overall leaching time, which can be beneficial for low reactivity ores or diluted acid concentrations.

# 25 3) Precipitation of ACH from the leachate by sparging of dry HCl gas. Figures 1 and 2 Step 30

Leachate containing solubilized chloride metals is sparged with a dry gas containing HCl in a crystalizing reactor maintained at temperature between 50°C and 90°C until the concentration of HCl in the solution reaches 30wt%. At this concentration, the maximum solubility of Al<sup>3+</sup> is 3 g/L,

30 thus excess Al<sup>3+</sup> present in the starting leachate precipitates as AlCl<sub>3</sub>.6H<sub>2</sub>O, an hydrated salt that can be separated from the acid solution containing dissolved Ca<sup>2+</sup>, Mg<sup>2+</sup> and Fe<sup>2/3+</sup> among others. As explained above ("The invention") a preferred embodiments for the present process is to perform a fractional or multi-stage precipitation process (Figures 1 and 2).

# 4) Calcination of ACH for HCl gas recovery and production of $Al_2O_3$ . Figures 1 and 2 -Step 40

To recover HCl gas and produce  $Al_2O_3$ , ACH solid is heated in a two steps calcination process. In the first calciner, ACH is decomposed at temperature between 400 and 550°C to produce HCl gas using

- 5 indirect heating to avoid contamination of the HCl gas. In the second step, the aluminium hydroxide is heated at temperature above  $1000^{\circ}$ C in a circulating fluidized bed system or in a rotating kiln in order to produce Al<sub>2</sub>O<sub>3</sub> with a low LOI and low alpha form.
- 10

# 5) Iron extraction by liquid/liquid separation method (optional). Figure 2 - Step 80

It is an optional step to separate the iron ions from the aqueous solution with a liquid/liquid extraction method with the process configuration according to claim 10 and shown in Figure 2.

# 6) Acid recovery by evaporation. Figures 1 and 2- Step 80

After sparging and separation of the precipitated ACH, the aqueous solution contains at least
20wt% HCl, together with the remaining metal chlorides in solution. HCl is recovered from the leachate solution by evaporation or distillation. The process strongly benefit from the high
chlorides metal concentrations in the feed stream as chlorides act as «azeotropazeotrope breaker» and allows for a recovery of concentrated HCl with less energy, The distillation is pursued until all the HCl are recovered. If necessary, precipitated solids during pH increase such as Al(OH)<sub>3</sub>
are filtrated from the aqueous phase and dissolved in the leaching reactor.

# Precipitation of carbonatecarbonates from the metalcalcium-chloride-rich solution with combined HCl extraction. Figures 1 and 2- Steps 60

The metal<u>calcium</u>-chloride-rich aqueous solution is contacted with an organic solution containing a tertiary or a quaternary amine dissolved in one or a mixture of hydrocarbon dilutent. While mixing

the organic and the aqueous phase, the reactor is pressurized with a CO<sub>2</sub> containing gas at a pressure of at least 10 bars and at ambient temperature. After a reaction time between 3 and 20 minutes, the reactor vessels is depressurized and the aqueous phase containing solid metalcalcium carbonate separates from the organic phase containing the HCl loaded amine. After separation of the two liquid phases, the carbonate-rich solution is pumped to the deposition site or filtered to recover the solid carbonate.

8) HCl and amine regeneration from the loaded amine. Figures 1 and 2- Step 70

The organic solution loaded with HCl (ammonium chloride salt/amine hydrochloride salt) is heated at temperature above 150°C, to decompose the amine HCl complex and generate a HCl-containing gas that can be recirculated to the process. The distillation can be carried out using  $N_2$  or any other inert carrying gas. After distillation, the regenerated amine is recirculated to the carbonate

# 5 precipitation stage.

Alternatively, the HCI-loaded amine can be regenerated by contacting the organic phase with a concentrated aqueous basic solution and recirculated to the PCC production step. The produced NaCI can be used as feed solution for in a chloro-alkali ectrolyser to produce HCI and NaOH.

#### 10

# Examples

All the process steps have been tested at laboratory scale, and the first core step at pilot scale (leaching of Al-rich mineral) showing the technical feasibility. The following examples will serve only to illustrate the practice of this invention and provide a useful description of the principles

15 and conceptual aspects of this invention, not limiting the invention to these particular embodiments.

# Example 1 Leaching.

In a reactor of 100 liters design capacity, 15kg of anorthosite slurry in water (33wt% water) is mixed with 38 l of a preheated HCl solution (22wt%HCl) at 70°C. The anorthosite particle size is

20 300 micron. The mixture is further heated up to 140°C (with steam flowing through the reactor steam-jacket), building a pressure of 2.5 bar, under vigorous mechanical stirring. The total reaction time from the mixing point is 5 hours. Samples of the mixture are taken at 2.5 and 5 hours, filtered and analysed by ICP-MS (Ion Coupled Plasma with Mass Spectrometer). The measured aluminium recovered from the anorthosite to the liquid fraction is 88wt% at 2.5 h and 95wt% at 5 hours.

# 25 Example 2 HCl extraction and metal carbonatecalcium carbonates precipitation with different amines.

Several types of amine solutions were tested to evaluate the influence of the chemical nature of the active organic phase on the PCC technology. The chemical properties of the amine function are related to the capacity of the free electron pair of the N atom to form hydrogen bonds. In case of

30 an acid extraction process, the strength of the amine (extraction capacity) is also determined by the availability of its unshared electron-pair to an electrophilic proton of the acid to extract. This availability is determined by the inductive effect of the atoms and chains bonded to the N atom (Eyal et al. (1991)). Due to the inductive effect of substituting H by an aliphatic chain, tertiary amines are expected to have a higher basic strength than primary and secondary amines. In addition, basicity is expected to increase with the length of the aliphatic chain.

In this technology, the basic strength of the amine is also expected to play an important role in its ability to react with  $CaCl_2$  and  $HCO_3^{2}$  to produce the ammonium hydrochloride salt and  $CaCO_3$ . The

- 5 basic strength of the amine function has to be sufficiently high to balance the acidification of the aqueous solution due to the dissolution of CO<sub>2</sub> and formation of carbonic acid and allow the formation of CaCO<sub>3</sub>. However, amine with an higher basic strength will form more stable amine hydrochloride complex that will require more energy to decompose or thermolyse in the regeneration step.
- 10 Tertiary amines (R3N) with various carbon chain length, R from 4 to 12 carbons were here tested for the precipitation of  $CaCO_3$  from a  $CaCl_2$  solution.

The following amines with straight carbon chains were assessed:

15

C4 : Tri-butyalmine (TBA); C6: Tri-hexylamine (THA); C8: Trioctylamine (TnOA), Tri-iso-octylamine (TiOA) and C12: Tri-docdecylamine (TDA). In addition a branched tertiary amine solution with 8C chains was tested for the PCC reaction: Tri-2etyl-hexylamine (TEHA).

Tests with TBA showed a close to 100% conversion of the amine into ammonium hydrochloride salt thanks to its low viscosity and very efficient PCC formation. However, in its salt form, the amine is soluble in water, rendering challenging the regeneration of the HCl and the TBA without evaporation or post-processing of a large quantity of water.

20 THA and TOA in identical experimental conditions (50% amine in 1/3 decanol-2/3 Asol dilutent, Cato-amine ratio=2, time, pCO<sub>2</sub>), presented close to identical high efficiency yields.

Despite its stronger basicity and higher thermal stability, TDA (12 C) is a more challenging organic amine to use in this process due to its higher viscosity. In the same dilution conditions as the other amines, a lower PCC yield of 13% was obtained, due to the difficulty to properly contact the

25 aqueous and organic phases in the laboratory vessels. In a future work, additional tests in more diluted conditions (<50% amine in solvent) should be evaluated.</p>

Finally the 8C branched amine, TEHA, did not show any precipitation of  $CaCO_3$  or HCl during testing despite its expected stronger basicity and low viscosity. A possible explanation for this behavior might be a steric hindrance of the amine function by the branched aliphatic groups,

30 reducing the accessibility of the electron pair for co-precipitation of CaCO3 and HCl extraction. A particular example of potential modifier is the use of an organic acid in addition of the amine and the dilutent. When added to the extractant, those compounds were proved to increase the selectivity and reversibility of the amine (Eyal et al. (1982)). Other acid extractants such as quaternary amines (Aliquat) or phosphine-based acid extractant such as TBP might also be interesting candidates for the liquid extraction process with CaCO<sub>3</sub> precipitation that need further experimental work. A more thorough investigation on the effect of these amines on the technology can be performed to identify the critical parameters and the antimal conditions for this new CO<sub>2</sub> storage technology.

5 optimal conditions for this new CO<sub>2</sub>-storage technology.

From the tested amines, efficiencies over 80wt% of CaCO<sub>3</sub> precipitation were achieved in only one step with TiOA diluted in Decanol/Asol, and with THA diluted in Decanol/Asol and in Dodecane. An efficiency of 76wt% was achieved with TOA in Decanol/Asol, which could be enough when applying several steps, if the regeneration of the amine results energetically advantageous.

10

### Example 3 Calculation of the necessary stages for HCl extraction.

From the different experimental tests, one representative case was selected to determine the required countercurrent stages by applying an adapted McCabe Thiele diagram method. In this

15 case, the organic phase was the Tri-iso-octylamine (TiOA) with an amine to organic dilutants ratio of 1:1 (vol) and decanol and asol as dilutants in a proportion of 2:1 vol.

The McCabe-Thiele method is widely used in metallurgy for pre-engineering and pilot design since it gives a good approximation of the volumes, stages, concentrations, etc. with relatively low complexity. The distribution curves or equilibrium isotherms are experimentally obtained under

20 the process conditions, and represent the final concentration of a dissolved component in the two phases (aqueous and organic) when the mixture reaches the equilibrium. The proof-of-concept based on process solutions and the generation of accurate engineering data can only be done in a pilot plant, though its efficiency is calculated by comparison with laboratory curves and data.

In this process, the method had to be adapted to the unique nature of the reaction, which is not a conventional liquid/liquid organic extraction, but a 4-phase extractive/chemical reaction. Thus, the calcium does not remain "dissolved" in the organic phase, but precipitates back to the aqueous phase as calcium carbonate, so the corresponding theoretical HCl in the aqueous solution has to be calculated from the chemical equation.

Therefore, a set of experiments with fixed CaCl<sub>2</sub> concentration (0.875 Molar), varying the organic
to aqueous phase (O/A from 2.45 to 5.25) and bubbling CO<sub>2</sub> at 50 bar during 20 minutes to reach
equilibrium were performed to determine the precipitated calcium carbonate.

The expected  $CaCl_2$  concentration of the feed stream in the global process (coming from the sparging and evaporation step) was determined, corresponding to 0.09 kg (HCl)/kg (water).

Considering an efficiency of 90% acid extraction, the number of counter current steps were estimated.

From these results, two counter-current extraction steps were calculated for those conditions, and their specific stream compositions were obtained and considered for mass and energy balances,

5 for the list of equipment implementation and cost estimation of the process. It is important to highlight that these results are specific for this extraction conditions and amine type, though they prove the realistic number of steps needed for the acid extraction.

## Claims:

1. A process for alumina and carbonate production from aluminium rich materials with integrated  $CO_2$  utilization, comprising the following steps:

- 5 I. crushing and milling of the Al-rich materials,
  - II. leaching of the crushed materials in acid to produce a metal chloride solution
  - III. separation of the unreacted solid and the metal chloride solution
  - IV. separation of  $Al^{3+}$  from the metal chloride solution by crystallization of  $AlCl_3 \cdot 6H_2O$
  - V. production of  $Al_2O_3$  by calcination of  $AlCl_3 \cdot 6H_2O$  with HCl recovery
- 10 VI. utilization of  $CO_2$  to precipitate metal<u>calcium</u> carbonates from the metal chloride solution coming from the Al<sup>3+</sup> separation step
  - VII. regeneration of HCl and the extractive amine

# characterized in:

- leaching the material in step II with a concentrated mineral acid which is predominantly HCl,

 - separating the Al<sup>3+</sup> in step IV by precipitation of AlCl<sub>3</sub>·6H<sub>2</sub>O by increasing the HCl concentration in the metal chloride solution

- calcination in step V the AlCl<sub>3</sub>· $6H_2O$  in two sub-steps: First by indirect heating at temperature between 400 and 600°C to generate a HCl-rich gas followed by a second calcination at a temperature above 600°C to produce Al<sub>2</sub>O<sub>3</sub>

- mixing in step VI the AI-lean metal<u>calcium</u> chloride solution with an organic solution containing a selected amine and contacting the mixture with a CO<sub>2</sub>-containing gas, in order to extract HCl by formation of an ammonium chloride salt complex and to precipitate a metal<u>calcium</u> carbonate.
   separating the metal<u>calcium</u> carbonate in step VI, the remaining metal chlorides containing aqueous phase and the organic solution containing ammonium chloride.
- 25 processing thermally or chemically the organic solution in step VII to regenerate the amine for recirculation in the process.

2. Process according to claim 1, wherein the leaching is performed at a temperature in the range 80-180 °C, acid concentration is under 13M and a pressure below 10 bars, more preferably a concentration under 11M and a pressure not exceeding 5 bars.

30 3. Process according to claim 1, wherein a leaching time in the range from 0.5 to 24 hours is employed, more preferred from 1 to 10 hours, most preferred from 1 to 5 hours.

4. Process according to claim 1, wherein the crushing and milling is performed to a particle size smaller than 20 mm, more preferred to a size equal or under 0.5 mm.

5. Process according to claim 1, wherein Fe rich materials are removed by magnetic separation or optical sorting before step ii.

6. Process according to claim 1, wherein unreacted materials after leaching are separated by filtration and washed with a solution, chosen among acidic solution and water, in one or several

5 repetitions, to recover metal chlorides and unreacted acid and increase the SiO<sub>2</sub> purity.

7. Process according to claim 1, wherein  $AlCl_3 \cdot 6H_2O$  is precipitated from the Al-rich metal chloride solution by bubbling a HCl-containing gas, filtered and washed with a solution chosen among acidic solution and water.

8. Process according to claim 1, wherein AlCl<sub>3</sub>·6H<sub>2</sub>O is crystallized from the Al-rich metal chloride
solution by mixing with a concentrated HCl solution, filtered and washed with a solution chosen among acidic solution and water.

9. Process according to claim 1, wherein the precipitated  $AlCl_3 \cdot 6H_2O$  and impurities is partially redissolved with a solution, chosen among hydrochloric aqueous solution and water, filtered and recycled to the crystallization step iv.

15 10. Process according to claim 1, where the Al-lean metal chloride solution after the crystallization step is treated by liquid/liquid organic extraction to reduce the iron content.

11. Process according to claim 1, where the Al-lean metal chloride solution after the crystallization step is treated by distillation or <u>similarother</u> existing <u>concentrating</u> process for recovery of the free acid and increase of the metal chlorides concentration in the solution.

20 12. Process according to claim 1, wherein metal<u>calcium</u> carbonate is precipitated by contacting the Al-lean solution with a pressurized CO<sub>2</sub> containing gas and an organic solution containing a tertiary or a quaternary amine diluted in at least one organic solvent.

13. Process according to claim 12 wherein the HCl is regenerated from the organic solution by thermal treatment at temperature above 80°C to produce a HCl containing gas that can be

25 recirculated in the process

14. Process according to claim 12, where alternatively, the amine is regenerated by contacting the organic phase with a concentrated basic solution and recirculated into the precipitation step

15. Process according to claim 1 wherein the precipitated metal carbonate can be calcium carbonate, magnesium carbonate, sodium carbonate, sodium bicarbonate or any other metal

30 carbonate that promotes the extraction of HCl by the use of liquid-liquid extraction, according to claim 1



## Abstract

A process for alumina and carbonate production from aluminium rich materials with integrated  $CO_2$  utilization, comprising: comminuting and leaching Al-rich materials in concentrated HCI; separating unreacted material from metal chloride solution; separating Al<sup>3+</sup> from solution by crystallization of AlCl<sub>3</sub>·6H<sub>2</sub>O; calcination of AlCl<sub>3</sub>·6H<sub>2</sub>O with HCl recovery; precipitation of metal carbonatescalcium carbonate from  $CO_2$ ; regeneration of HCl and extractive amines; the Al<sup>3+</sup> separation the facilitated by increasing HCl concentration; the calcination being performed in two steps, one in the range 400 and 600°C to generate a HCl-rich gas and one above 600°C to produce Al<sub>2</sub>O<sub>3</sub>; for precipitating metal carbonatescalcium carbonate, mixing the metal chloride solution with an organic solution containing a selected amine and contacting the mixture with a  $CO_2$ - containing gas, thereby also extracting HCl by formation of an ammonium chloride salt complex; processing thermally or chemically the organic solution to regenerate the amine for recirculation.